

BRADY B-193 BRADYGUARD (TM) PROPERTY NAMEPLATES

TDS No. B-193
Effective Date: 06/29/2011

Description:

Brady Bradyguard (TM) Property Nameplates and Property ID Tags are a high quality anodized aluminum foil tag with a permanently etched legend that withstands both indoor and outdoor exposure.

Details:

Use:

Brady B-193 tags are used as a durable asset identification tag, where consecutive numbering may be needed in an office or manufacturing environment.

Substrate Type:

Anodized aluminum

Adhesive Type:

- 3M #467 - permanent pressure sensitive adhesive for most smooth non-plastic surfaces.
- 3M #468 - permanent pressure sensitive adhesive for rough or textured non-plastic surfaces.
- 3M #9471 permanent pressure sensitive adhesive for smooth plastic surfaces.
- 3M #9472LE - permanent pressure sensitive adhesive for textured plastic surfaces.

Standard Material Colors:

Black, Light Blue, Dark Blue, Brown, Bronze, Dark Green, Gold, Dark Red, Flame Red, Purple, Yellow.

Total Thickness (PSTC-33):

- 3M #467 - .005" (0.127mm)
- 3M #468 - .008" (0.203 mm)
- 3M #9471 - .005" (0.127 mm)
- 3M #9472LE - .008" (0.203 mm)

Adhesive Properties:

Adhesion to Stainless Steel (PSTC-1) (Avg.)

	3M #467	3M #468	3M #9471	3M #9472LE
15 minute dwell	destroyed	destroyed	destroyed	destroyed
Ultimate Dwell (72 hours)	destroyed	destroyed	destroyed	destroyed

Tack - ASTM D 2979 (Avg.)

	3M #467	3M #468	3M #9471	3M #9472LE
15 minute dwell	1618 g (15.9 N)	1538 g (15.1 N)	1234 g (12.1 N)	1750 g (17.2 N)

Abrasion Resistance (Method 5306 of U.S. Federal Test Method Std. No. 191A):

CS-10 Wheels, 500 g wts.
Legend withstands up to 1000 cycles

60° Gloss:

38 Gardner Units

Minimum Application Temperature:

40°F (4°C)

Service Temperature:

-40°F to 300°F (-40°C to 149°C)

Application Temperature:

40°F (4°C)

Average Outdoor Durability:

3-5 years (Average expected outdoor life of product will depend on user definition of failure, climatic conditions, mounting techniques and material color.)

Chemical Resistance:

REAGENT	7 DAY IMMERSION	DIP TEST	RUB TEST
30% Sulfuric Acid	F	F	NE
10% Sulfuric Acid	F	F	NE
30% Hydrochloric Acid	F	F	NE
10% Hydrochloric Acid	F	F	NE
50% Sodium Hydroxide	F	F	NE
10% Sodium Hydroxide	F	F	NE
Methyl Ethyl Ketone	F	NE	NE
Acetone	F	NE	NE
Toluene	F	F	NE
1,1,1-Trichloroethane	F	NE	NE
Methanol	F	NE	NE
Isopropyl Alcohol	NE	NE	NE
Heptane	F	NE	NE
Mineral Spirits	F	NE	NE
Kerosene	F	NE	NE
Diesel Fuel	F	NE	NE
ASTM #3 Oil	NE	NE	NE
SAE 20 Oil	NE	NE	NE
10% Sodium Chloride	F	NE	NE
Alconox®	NE	NE	NE
Bleach	NE	NE	NE
Water	NE	NE	NE

NE = No Effect

F = Failed (affected Sample)

7 Day Immersion: Immersed in reagent for 7 days.

Dip Test: Five 10 minute dips in reagent with 30 minute recovery.

Rub Test: Rubbed sample for 1 minute with swab soaked in reagent.

Product testing, customer feedback, and history of similar products, support a customer performance expectation of at least **two years from the date of receipt** for this product as long as this product is stored in its original packaging in an environment *below 80°F (27°C) and 60% RH*. We are confident that our product will perform well beyond this time frame. However, it remains the responsibility of the user to assess the risk of using such product. We encourage customers to develop functional testing protocols that will qualify a product's fitness for use in their actual applications.

Trademarks:

Alconox® is a registered trademark of Alconox Co.

Signmark® is a registered trademark of Brady Worldwide, Inc.

Fed. Spec.: United States Federal Specification (U.S.A.)

PSTC: Pressure Sensitive Tape Council (U.S.A.)

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2016 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289