

BRADY B-7578 THERMAL TRANSFER PRINTABLE MATTE WHITE POLYESTER LABEL STOCK

TDS No. B-7578
Effective Date: 05/29/2015

Description:

GENERAL

B-7578 is a matte white polyester film with a permanent acrylic pressure sensitive adhesive and a topcoat specifically formulated for thermal transfer printing.

APPLICATIONS

B-7578 is designed for applications such as topside of printed circuit boards and rating plates that utilize high quality/density alphanumeric, barcodes and graphics.

RECOMMENDED RIBBONS

Recommended ribbons are the Brady Series R-7960, R-7961 and R-7962 ribbons for optimal print performance.

ROHS Environmental Compliance

Brady B-7578 is RoHS compliant to RoHS directive 2011/65/EU

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 - Substrate - Adhesive - Total	0.0584 mm (0.0023 in) 0.0203 mm (0.0008 in) 0.0787 mm (0.0031 in)
Adhesion to: -Stainless Steel	ASTM D 1000 20 minute dwell 24 hour dwell	48 N/100 mm (44 oz/in) 54 N/100 mm (49 oz/in)
-Polypropylene	20 minute dwell 24 hour dwell	34 N/100 mm (31 oz/in) 47 N/100 mm (43 oz/in)
Tensile Strength and Elongation	ASTM D 1000 -Machine	765 N/100 mm (44 lbs/in), 90%
Tack	ASTM D 2979 Polyken™ Probe Tack 1 second dwell	526 g (19 oz)

Performance properties tested on B-7578 with series R-7960, R-7961 and R-7962 using the BradyPrinter™ 300X thermal printer. Printed samples were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environments. Unless noted, results are the same for all ribbons.

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
Short Term High Service Temperature	5 minutes at 180° C (356° F)	No visible effect at 180° C Label shrinkage at 210° C
Long Term High Service Temperature	30 days at 100° C (212° F)	No visible effect at 100° C Label yellowed at 120° C
Low Service Temperature	30 days at -40° C (-40° F)	No visible effect
Humidity Resistance	30 days at 37° C (100° F), 95% R.H.	No visible effect
UV Light Resistance	30 days UV Sunlighter™ 100	Severe yellowing of topcoat
Weatherability	ASTM G 26 30 days in Xenon Arc Weatherometer	Slight topcoat discoloration and chalking.
Salt Fog Resistance	ASTM B 117 30 days in 5% salt fog solution chamber	No visible effect
Abrasion Resistance	Method 5306 US Federal Test 191A, Test consisted of 100 Cycles R-7960 (CS10 + 250 g / arm)	Moderate Fading

R-7961 (CS10 + 250 g / arm)
R-7962 (CS10 + 250 g / arm)

Moderate Fading
Very Slight Fading

PERFORMANCE PROPERTY

CHEMICAL RESISTANCE

Samples printed with Series R-7960, R-7961 and R-7962 ribbons using a BradyPrinter™ THT Model 300X thermal transfer printer. Samples laminated to aluminum panels and allowed to dwell 24 hours prior to testing. Test conducted at room temperature. Testing consisted of 5 cycles of 10 minute immersions in the specified test fluid followed by a 30 minute recovery period. After final immersion, samples rubbed 10 times with cotton swab saturated with test fluid.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE			
	LABEL STOCK	R-7960	R-7961	R-7962
Isopropylalcohol	N.V.E.	N.V.E.	N.V.E.	N.V.E. w/o rubbing, S.F. w/ rubbing
Aceton	N.V.E.	Gone w/o rubbing	Gone w/o rubbing	Gone w/o rubbing
Ethyl Methyl Ketone	N.V.E.	Gone w/o rubbing	Gone w/o rubbing	Gone w/o rubbing
n-Hexane	N.V.E.	N.V.E.	N.V.E.	N.V.E.
1,1,1-Trichloroethane	N.V.E.	N.V.E. w/o rubbing, Gone w/ rubbing	N.V.E. w/o rubbing, Gone w/ rubbing	N.V.E. w/o rubbing, SL.F. w/ rubbing
Toluene	Slight chalking	SL.F. w/o rubbing, Gone w/ rubbing	SL.F. w/o rubbing, Gone w/ rubbing	N.V.E. w/o rubbing, Gone w/ rubbing
Diesel	N.V.E.	N.V.E.	N.V.E.	N.V.E.
Gasfuel	N.V.E.	N.V.E. w/o rubbing, SL.F. w/ rubbing	N.V.E. w/o rubbing, S.F. w/ rubbing	N.V.E.
Iso-Octane	N.V.E.	N.V.E.	N.V.E.	N.V.E.
Alcohol Mixture*	N.V.E.	N.V.E.	N.V.E.	N.V.E.
Skydrol® 500B-4	N.V.E.	S.F. w/o rubbing, Gone w/ rubbing	S.F. w/o rubbing, Gone w/ rubbing	M.F. w/o rubbing, Gone w/ rubbing
Mineral Oil	N.V.E.	N.V.E.	N.V.E.	N.V.E.
Sulfuric acid (10%)	N.V.E.	N.V.E.	N.V.E.	N.V.E.
Sodium Chloride (10%)	N.V.E.	N.V.E.	N.V.E.	N.V.E.
Sodium Hydroxide (10%)	Topcoat comes off	Topcoat gone	Topcoat gone	Topcoat gone
Water	N.V.E.	N.V.E.	N.V.E.	N.V.E.

* Alcohol mixture: 50% Methanole, 30% Ethanole and 20% Water.

N.V.E.: No visible effect
SL.F.: Slight fading
M.F.: Moderate fading
S.F.: Severe fading

Product testing, customer feedback, and history of similar products, support a customer performance expectation of at least **two years from the date of receipt** for this product as long as this product is stored in its original packaging in an environment *below 80°F (27°C) and 60% RH*. We are confident that our product will perform well beyond this time frame. However, it remains the responsibility of the user to assess the risk of using such product. We encourage customers to develop functional testing protocols that will qualify a product's fitness for use in their actual applications.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)
BradyPrinter™ is a trademark of Brady Worldwide, Inc.
Fed. Spec.: United States Federal Specification (U.S.A.)
Polyken™ is a trademark of Testing Machines Inc.
Skydrol® is a registered trademark of the Monsanto Company
Sunlighter™ is a trademark of the Test Lab Apparatus Company

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2016 W.H. Brady, N.V. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady Europe | Industriepark C3 Lindestraat 20 | B9240 Zele | Belgium | Tel: +32 52.45.7811 | Fax: +32 52.45.7812