



## Technical Data Sheet

### BRADY B-8459 THERMAL TRANSFER PRINTABLE MATTE WHITE POLYESTER LABEL STOCK

TDS No. B-8459  
Effective Date: April 16, 2018

Description: GENERAL  
Print Technology: Thermal Transfer  
Material Type: White Polyester Finish: Matte  
Adhesive: Permanent Acrylic

#### APPLICATIONS

Designed for applications such as topside of printed circuit boards and rating plates that utilize high quality/density alphanumerics, barcodes and graphics.

#### RECOMMENDED RIBBONS

Brady Series R4900  
Brady Series R6000 Halogen Free (Previously known as R6000HF)

#### REGULATORY/AGENCY APPROVALS

UL: B-8459 is UL Recognized to UL 969 Labeling and Marking Standard when printed with Brady Series R4900, and R6000 Halogen Free black ribbons. See UL file MH17154 for specific details.

cUL: B-8459 is a cUL Recognized Component when printed with the Brady R6000 Halogen Free Series and R4900 Series black ribbons. See UL file PGJ12.8-MH17154 for specific details. UL information can be accessed on line at UL.com. Search in Certifications area.

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total	0.0020 inch (0.0508 mm) 0.0008 inch (0.0203 mm) 0.0028 inch (0.0711 mm)
Adhesion to: -Stainless Steel	ASTM D 1000 20 minute dwell 24 hour dwell	57 oz/inch (62 N/100 mm) 61 oz/inch (67 N/100 mm)
-Polypropylene	20 minute dwell 24 hour dwell	49 oz/inch (54 N/100 mm) 50 oz/inch (55 N/100 mm)
Tack	ASTM D 2979 Polyken™ Probe Tack (1 second dwell, 1 cm/sec separation)	46 oz (1310g)

Performance properties tested on B8459 printed with R4900, and R6000 Halogen Free black ribbons. Printed samples were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environments. Unless noted, results the same for both ribbons.

PERFORMANCE PROPERTIES	TEST METHOD	TYPICAL RESULTS
Short Term High Service Temperature	5 minutes at various temperatures	No visible effect to label at 180°C. Label shrinkage at 210°C;
High Service Temperature	30 days at various temperatures	No visible effect to label at 100°C.

		Slight discoloration at 120°C;
Low Service Temperature	30 days at -40°C	No visible effect
Humidity Resistance	30 days at 100°F (37°C) and 95% relative humidity.	No visible effect
UV Light Resistance	30 days in UV Sunlighter™ 100	No visible effect
Weatherability	ASTM G155, Cycle 1 30 days in Xenon Arc Weatherometer	No visible effect
Salt Fog Resistance	ASTM B 117 30 days in 5% salt fog solution chamber	No visible effect
Abrasion Resistance	Taber Abraser, CS10 grinding wheels, 250 g/arm (Fed. Std. 191A, Method 5306)	R4900: Print legible after 30 cycles R6000 Halogen Free: Print legible after 125 cycles

<b>PERFORMANCE PROPERTY</b>	<b>CHEMICAL RESISTANCE</b>
-----------------------------	----------------------------

Samples were printed with Series R4900 and, R6000 Halogen Free ribbons. Samples were laminated to aluminum panels and allowed to dwell 24 hours prior to testing. Testing was conducted at room temperature and consisted of 30 minute immersions in the specified test fluid. After immersion, the samples were removed from the test fluid and the printed image rubbed 10 times with a cotton swab saturated with the test fluid. The rating scale below shows the effect to the quality of the print for each sample.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
	EFFECT TO LABEL STOCK	R4900	R6000 Halogen Free
Methyl Ethyl Ketone	No visible effect	Print removed when immersed	Print removed when immersed
Isopropyl Alcohol	No visible effect	No visible effect	No visible effect
Mineral Spirits	No visible effect	No visible effect	No visible effect
SAE 20 WT Oil @ 70°C	No visible effect	No visible effect	No visible effect
Mil 5606 Oil	No visible effect	No visible effect	No visible effect
Speedi Kut Cutting Oil 332	No visible effect	No visible effect	No visible effect
Gasoline	No visible effect	No visible effect	No visible effect
Rust Veto® 342	No visible effect	No visible effect	No visible effect
Northwoods™ Buzz Saw Degreaser	No visible effect	Print removed when rubbed	Print removed when rubbed
Deionized Water	No visible effect	No visible effect	No visible effect
5% Salt Solution	No visible effect	No visible effect	No visible effect
3% Alconox® Detergent	No visible effect	No visible effect	No visible effect
10% Sodium Hydroxide Solution	No visible effect	No visible effect	No visible effect
10% Sulfuric Acid Solution	No visible effect	No visible effect	No visible effect

Shelf life is one year from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

**Trademarks:**

Alconox® is a registered trademark of Alconox Co.  
BradyPrinter™ is a trademark of Brady Worldwide, Inc.

Northwoods™ is a trademark of the Superior Chemical Corporation  
Polyken™ is a trademark of Testing Machines Inc.  
Rust Veto® is a registered trademark of the E.F. Houghton & Co.  
Sunlighter™ is a trademark of the Test Lab Apparatus Company ASTM:  
American Society for Testing and Materials (U.S.A.)  
SAE: Society of Automotive Engineers (U.S.A.)  
UL: Underwriters Laboratories Inc. (U.S.A.)  
cUL: Underwriters Laboratories Inc. (U.S.A.)  
All S.I. Units (metric) are mathematically derived from the U.S.  
Conventional Units

Note: All values shown are averages and should not be used for specification purposes.  
Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

#### **WARRANTY**

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2018 Brady Worldwide, Inc. | All Rights Reserved  
Material may not be reproduced or distributed in any form without written permission.

---

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax:  
800-292-2289